

Chemical Resistance (cont.)

Chemical	Concentration	Conditions		Chemical	Concentration	Conditions	
		20°C 68°F	60°C 140°F			20°C 68°F	60°C 140°F
Hydrofluoric acid	40% aq. soln	1	4	Photographic emulsions		1	1
Hydrofluoric acid	60% aq. soln	5	5	Photographic fixing soln		1	1
Hydrofluoric acid	conc.	5	5	Picric acid	1% w/w in water	1	1
Hydrogen		1	1	Picric acid	10% w/w in alcohol	1	4
Hydrogen bromide anhydrous		1	4	Potassium hydroxide	1% aq. soln	1	1
Hydrogen chloride anhydrous		1	4	Potassium hydroxide	10 aq. soln	1	1
Hydrogen fluoride		1	4	Potassium hydroxide	conc aq. soln	1	5
Hydrogen peroxide	3% (10 vol)	1	4	Potassium salts		1	1
Hydrogen peroxide	12%(40 vol)	1	4	Propane		2	2
Hydrogen peroxide	30% (100 vol)	1	4	Propylene dichlorid		5	5
Hydrogen peroxide	90% and above	1	4	Salicylic acid		4	4
Hydrogen sulfite		1	4	Sea water		1	1
Iodine	soln in potassium	4	4	Soap solution		1	4
Iodine	iodide	5	5	Sodium hydroxide	1% aq. soln	1	4
Lacquer solvents		3	5	Sodium hydroxide	10% aq. soln	1	3
Lactic acid	10%	1	4	Sodium hydroxide	40% aq. soln	1	5
Lactic acid	100%	5	5	Sodium hydroxide	conc aq. soln	1	5
Lactic acid		1	4	Sodium hypochlorid	15% act. cl.	1	3
Lauryl alcohol		1	1	Sodium salts		1	1
Lead salts		1	1	Sulphur dioxide	dry	1	1
Magnesium salts		1	1	Sulphur dioxide	moist	4	5
Manganese suphate	conc. soln	1	1	Sulphur dioxide	liquid	4	5
Mercuric chloride		5	5	Sulphuric acid	10%	1	1
Methyl chloride		5	5	Sulphuric acid	45%	1	1
Methyl ethyl ketone		5	5	Sulphuric acid	50%	1	3
Methylene chloride		5	5	Sulphuric acid	60%	3	3
Milk		1	4	Sulphuric acid	98%	3	3
Mineral oils		2	2	Sulphuric acid	fuming	5	5
Mixed acids (sulphuric/nitric)	various proportions	4	5	Sulphurous acid	30%	1	4
Molasses		1	1	Tallow		1	4
Naphtha		5	5	Tannic acid		1	4
Naphthalene		5	5	Tanning extracts		1	4
Nitric acid	10%	1	4	Tartaric acids		1	4
Nitric acid	25%	1	4	Tetraethyl lead		1	4
Nitric acid	50%	1	3	Tetrahydrofuran		5	5
Nitric acid	70%	3	5	Tetralin		5	5
Nitric acid	95%	5	5	Toluene		5	5
Nitrobenzene		5	5	Transformer oil		2	5
Nitrogen fertilizers		1	4	Trichloroethane		5	5
Nitrous fumes	moist	4	5	Triethanolamine		1	1
Oleic acid		1	4	Trichlorethylene		5	5
Oxalic acid		1	4	Triethylamine		4	4
Oxygen		1	1	Turpentine		4	4
Ozon		1	4	Urea		1	4
Palmitic acid		1	4	Vegetable oils		1	4
Paraffin		3	4	Vinegar		1	4
Petrol		2	2	Vinyl acetate		5	5
Petrol benzene mixture	80:20:00	5	5	Water		1	1
Phenol		4	5	Wetting agents		1	1
Phosphoric acid	20% aq. soln	1	1	Wines ans spirits	all conc.	1	4
Phosphoric acid	30% aq. soln	1	1	Xylene		5	5
Phosphoric developers	30% aq. soln	1	1	Zink salts		1	1

Legend:

1 Satisfactory

2 Recomanded for the service and conditons shown for oil hose.

3 The material may be considered for use when alternativ materials are unsatisfactory and whenlimited life is acceptable.

4 When pvc is to be used whit such chemicals, full-scale trials under realistic conditions are particularly necessary.

5 Unsatisfactory